MOTIP Polyester Resin

Technical Information



Fyll dypere skader som hull i overflater av stål, aluminium, tre, betong og polyester på bilen din i kombinasjon med en glassfibermatte og glassfiberfleece med MOTIP 2-komponent Polyester Resin. Harpiksen er egnet for å lage gjenstander som det kreves en form for. Polyesterharpiks er elastisk og motstandsdyktig mot kjemikalier og vær. MOTIP Polyester Resin har utmerket vedheft og er etter herding kun mekanisk slipbar.

Bestillingsnummer: 000071, 000072

Kvalitet og egenskaper

Elastisk
Motstandsdyktig mot kjemikalier og værpåvirkninger
Utmerket vedheft
Kun mekanisk slipbar

Fysiske og kjemiske data

Base: Polyester harpiks
Kolourname: yellow
Lukt: Karakteristisk
Grad av glans: matt, 10 ±2
Kan slipes etter: 40 min
Overflater: Steel, aluminium, wood, concrete, polyester
Minimum arbeidstemperatur: 10 °C
Maksimal arbeidstemperatur: 25 °C
Flammepunkt: 31 °C
Potlife: 8-10 min
Hardere prosentandel: 2.5 %
Lagringsstabilitet: 2 y
Innhold:
- 250 G
- 1,00 KG

European Aerosols GmbH, Kurt-Vogelsang-Straße 6, 74855 Haßmersheim – info-de@european-aerosols.com
European Aerosols B.V., Wolfraamweg 2, NL-8471 XC Wolvega – info-nl@european-aerosols.com

Hvordan bruke

Les instruksjonene nøye før bruk.
Best resultat får du mellom 15 til 25 °C.
Overflaten skal være ren, tørr og fri for fett. Fjern løs gammel lakk og rust og slip overflaten med sandpapir.
Skjær glassfibermatten i riktig størrelse, med en liten overlapping. Bland den nødvendige mengden polyesterharpiks med herder
Smør kantene på hullet som skal fylles med polyesterharpiks og påfør glassfibermatten.
Smør matten med polyesterharpiks, start i kanten.
Påfør deretter glassfiberfleezen og smør med polyesterharpiks. Avhengig av skaden kan denne prosedyren gjentas.
Etter herding, bare mekanisk slipbar. Sand og bruk en fin kitt når ønskelig.
Tørketiden avhenger av omgivelsestemperaturen.
Rengjør verktøyene som brukes, direkte etter bruk. Ikke oppbevar overskuddsmaterialet, blandet med herder, i boksen.

Environmentally sound

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

Disposal

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as “special refuse”.

Marking/Labelling

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

As of August 6, 2025 – This release replaces all eventually earlier issued versions.

European Aerosols GmbH, Kurt-Vogelsang-Straße 6, 74855 Haßmersheim – info-de@european-aerosols.com
European Aerosols B.V., Wolfraamweg 2, NL-8471 XC Wolvega – info-nl@european-aerosols.com