MOTIP Alu-Zinc Spray

Technical Information



Hurtigtørkende Alu-Sinkspray med gode fyllingsegenskaper og utmerket vedheft for behandling av galvanisert og ubehandlet stål. Alu-sinkspray gir enestående katodisk korrosjonsforebygging, er punktsveisbar og er motstandsdyktig mot bensin, kjemikalier og vær. MOTIP Alu-Zinc Spray er varmebestandig til 250 °C.

Bestillingsnummer: 04059

Kvalitet og egenskaper

Fremragende katodisk korrosjonsforebygging
Gode fylleegenskaper
Motstandsdyktig mot bensin, kjemikalier og værpåvirkninger
Hurtigtørkende
Punkt-sveisbar
Utmerket vedheft

Fysiske og kjemiske data

Base: Epoksy-ester
Kolourname: alu-silver
Lukt: Karakteristisk
Grad av glans: matt, 10 ±2
Effektivitet: 400 ML – 1.25 - 1.75 m²
Støvtørr: 10 - 15 min
Tørr å ta på: 20 - 30 min
Helt tørr: 24 h
Overstrøkbar: 24 h
Overflater: Treat galvanised and untreated steel.
Minimum arbeidstemperatur: 10 °C
Maksimal arbeidstemperatur: 25 °C
Flammepunkt: n.a.
Temperaturbestandighet: 250 °C
Lagringsstabilitet: 10 y
Innhold: 400 ML

European Aerosols GmbH, Kurt-Vogelsang-Straße 6, 74855 Haßmersheim – info-de@european-aerosols.com
European Aerosols B.V., Wolfraamweg 2, NL-8471 XC Wolvega – info-nl@european-aerosols.com

Hvordan bruke

Les instruksjonene nøye før bruk.
Overflaten skal være ren, tørr og fri for fett. Fjern løs gammel lakk og rust og slip overflaten med sandpapir.
Overflaten skal være ren, tørr og fri for fett. Boksen skal ha romtemperatur. Beste behandlingstemperatur er mellom 10 og 25 °C.
Rist boksen i 2 minutter og spray en prøve før bruk. Avstand til overflaten som skal behandles skal være ca. 25 til 30 centimeter.
Påfør alu-sinksprayen i flere tynne lag. Før du påfører neste lag, må du riste boksen igjen. Når ønskelig, etter tørking kan en grunning og en lakk påføres.
Rengjør spraydysen etter bruk (snu boksen opp ned og trykk på spraydysen i ca. 5 sekunder).
Tørketiden avhenger av omgivelsestemperaturen, luftfuktigheten og tykkelsen på den påførte lakken.

Environmentally sound

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

Disposal

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as “special refuse”.

Marking/Labelling

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

As of August 5, 2025 – This release replaces all eventually earlier issued versions.

European Aerosols GmbH, Kurt-Vogelsang-Straße 6, 74855 Haßmersheim – info-de@european-aerosols.com
European Aerosols B.V., Wolfraamweg 2, NL-8471 XC Wolvega – info-nl@european-aerosols.com