MOTIP 1K Epoxy Primer

Technical Information



MOTIP 1K Epoxy Primer er en universell primer av høy kvalitet for forbehandling av stål, rustfritt stål, galvanisert stål, aluminium og anodisert aluminium. Ekstremt egnet som primer for forbehandling før påføring av vannbaserte og løsemiddelbaserte baselakker og 1K og 2K toppstrøk.

Bestillingsnummer: 04119, 04120

Kvalitet og egenskaper

Anvendelig vått-i-vått
Utmerket dekning og fylleegenskaper
Kan belegges på nytt med alle malingssystemer
Flott korrosjonsbeskyttelse
Hurtigtørkende

Fysiske og kjemiske data

Base: 1K epoksyharpiks
Kolourname:
- dark grey
- grey

Lukt: Karakteristisk
Grad av glans: matt, 10 ±2
Effektivitet: 400 ML – 1.5 m²
Støvtørr: 10 - 20 min
Tørr å ta på: 20 - 30 min
Helt tørr: 120 min
Overstrøkbar: 120 min
Overflater: Steel, stainless steel, galvanized steel, aluminium and anodised aluminium
Minimum arbeidstemperatur: 10 °C
Maksimal arbeidstemperatur: 25 °C
Flammepunkt: n.a.
Temperaturbestandighet: 90 °C
Lagringsstabilitet: 10 y
Innhold:
- 400 ML
- 500 ML

European Aerosols GmbH, Kurt-Vogelsang-Straße 6, 74855 Haßmersheim – info-de@european-aerosols.com
European Aerosols B.V., Wolfraamweg 2, NL-8471 XC Wolvega – info-nl@european-aerosols.com

Hvordan bruke

Les instruksjonene nøye før bruk.
Overflaten skal være ren, tørr og fri for fett. Fjern løs gammel lakk og rust og slip overflaten med sandpapir.
Rist boksen i 2 minutter og spray en prøve før bruk. Beste behandlingstemperatur er mellom 10 og 25 °C.
Påfør epoksyprimeren i flere tynne lag, med en avstand på ca. 15 til 20 centimeter til overflaten som skal behandles.
Før du påfører neste lag, er det viktig å riste aerosolen igjen.
Rengjør spraydysen etter bruk (snu boksen opp ned og trykk på spraydysen i ca. 5 sekunder).
Tørketiden avhenger av omgivelsestemperaturen, luftfuktigheten og tykkelsen på den påførte lakken.

Environmentally sound

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

Disposal

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as “special refuse”.

Marking/Labelling

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

As of August 5, 2025 – This release replaces all eventually earlier issued versions.

European Aerosols GmbH, Kurt-Vogelsang-Straße 6, 74855 Haßmersheim – info-de@european-aerosols.com
European Aerosols B.V., Wolfraamweg 2, NL-8471 XC Wolvega – info-nl@european-aerosols.com