MOTIP Rust Converter Spray

Technical Information



MOTIP Rust Converter er en rustomformer og primer i ett arbeidstrinn. Utmerket egnet for restaurering av kjøretøy, maskiner og alle slags fasiliteter. Dette rustrestaureringssystemet på epoksyharpiksbasis smelter sammen med det nøytraliserte rustlaget til et metallisk-organisk jernkompleks. Dette svarte, svært kompakte beskyttelseslaget bygger opp primeren og er grunnlaget for den påfølgende, slitesterke lakkfinishen.

Bestillingsnummer: 04133

Kvalitet og egenskaper

Polymersystem med epoksy.
Ideell base for slitesterk lakkering.
Fri for bly og sinkkromat.
Brukervennlig
Svært effektiv
Varmebestandig opp til 160 °C.

Fysiske og kjemiske data

Base: Spesiell kombiharpiks
Kolourname: amber
Lukt: Karakteristisk
Minimum arbeidstemperatur: 10 °C
Maksimal arbeidstemperatur: 30 °C
Flammepunkt: n.a.
Lagringsstabilitet: 10 y
Innhold: 400 ML

Hvordan bruke

Les instruksjonene nøye før bruk.
Forbehandling: Overflaten skal være ren, tørr og fri for fett. Fjern løs rust og rust under overflaten.
Behandling: Overflaten skal være ren, tørr og fri for fett. Boksen skal ha romtemperatur. Beste behandlingstemperatur 10 til 25 °C. Rist boksen i 2 minutter og spray en prøve før bruk. Avstand til overflaten som skal behandles skal være ca. 25 til 30 centimeter.
Kan belegges på nytt etter ca. 6 timer.
Ekstra ovnvarming gjør beskyttelseslaget spesielt motstandsdyktig mot vann, saltvann og løsemidler. La den sprayede pelsen tørke i 15 minutter, og stek deretter i 15 minutter ved 160 °C.

Environmentally sound

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

Disposal

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as “special refuse”.

Marking/Labelling

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

As of August 5, 2025 – This release replaces all eventually earlier issued versions.

European Aerosols GmbH, Kurt-Vogelsang-Straße 6, 74855 Haßmersheim – info-de@european-aerosols.com
European Aerosols B.V., Wolfraamweg 2, NL-8471 XC Wolvega – info-nl@european-aerosols.com